



BISEAL[®]

FIBER

POLYPROPYLENE FIBERS

FOR REINFORCEMENT OF CONCRETE AND MORTAR



DESCRIPTION

BISEAL[®] FIBER are 100% virgin-polypropylene fibers without reprocessed olefin materials and produced in according to specifications ASTM C 1116 TYPE III GMP. These fibers are suitable for adding to concrete and mortars and have been specially studied for concrete industry. When fibers have been distributed homogeneously in the mixture, provide a reinforcement three-dimensional structure, which improves mechanical properties such as impact resistance, and also lead a long lasting for concrete and allow to control and minimize the cracking due to shrinkage. Three different versions are available according to the fiber length: 6, 12 and 18 mm.

APPLICATION FIELDS

- Plasters, pre-mixing and repair mortars.
- Pre-cast, screed concretes and generally pumped concrete and inclined casting concrete tubes.
- Provide concrete support and cohesion in sloping planes and/or slide mould placement.
- Avoid and control of cracking due to shrinkage for concrete applications with a low volume to surface ratio such as industrial floors, pipes, prefabricated elements, slabs, etc.
- Shotcrete mortars.
- Spalling phenomenon reducer.
- Making of concrete on roads and tunnels.
- Use in pre-cast concrete, extruded concrete, slabs and gunite.

ADVANTAGES

- Prevents the formation and the propagation of cracking by shrinkage.
- Increases the mechanical strengths for concretes or mortars; flexural, compression and impact.
- Compatible with other **BISEAL[®]** admixtures.
- Resistant to alkaline compounds present in concrete.
- Does not reduce the workability of the concrete or mortars. Does not absorb water.

- Replaces the secondary reinforcement bars, which are recommended to minimize the cracking in concrete surfaces.
- Reduces partially the permeability of the concrete.
- Non-toxic.

APPLICATION INSTRUCTIONS

Mixing and application

BISEAL[®] FIBER can be used in concrete industrial plants or in the job place. A suitable number of bags must be added directly into the mixer during the mixing step. However, avoid adding directly the fibers on the water. In order to get a better and homogeneous dispersion for the fibers into the concrete mixture, an increase in time for 5 minutes in the mixing is recommended.

CONSUMPTION

600 g per cubic meter of concrete or 140 g per bag of cement.

IMPORTANT INDICATIONS

- **BISEAL[®] FIBER** does not replace the reinforcement bars for structure which have been established in calculus.
- **BISEAL[®] FIBER** does not avoid carrying out methods for concrete curing if weather conditions require them.
- For further information or applications not included herein, consult out Technical Department.

PACKAGING

BISEAL[®] FIBER is supplied in bags of 600 g.

STORAGE

BISEAL[®] FIBER does not cause to deteriorate itself along the time. However, it should be stored in its original unopened packaging, in a dry and

covered place and protected from frost and sunlight.

Safety Data Sheet for **BISEAL® FIBER** is available by request.

SAFETY AND HEALTH

BISEAL® FIBER is non-toxic and non-corrosive product.

The final user must do disposal of the product and its empty containers according to official regulations.

TECHNICAL DATA

Product characteristics	
CE Marking, EN 14889-2	
Description: Polypropylene fiber packaged in water-soluble paper for concrete admixture.	
Colour	Natural
System	Monofilament
Section	Circular
Fiber length, (mm)	6, 12 and 18
Diameter, (µm)	31
Density, (g/m ³)	0,91
Humidity, (%)	2,65
Fluidity, EN ISO 1133:2006 (gr/10')	6,12
Young's elastic module, (kN/mm ²)	3,5
Tensile strength, (MPa)	300-400
Linear density, EN ISO 1973:1966 (dtex)	6,70 (±10%)
Tenacity, EN ISO 5079:1996 (cN/tex)	40±5
Ignition temperature, (°C)	>400
Deflection temperature, ISO 11357-3:1999 (°C)	110
Descomposition temperature, ISO 11357-3:1999 (°C)	280
Melting point, ISO 11357-3:1999 (°C)	164,41
Consistency of concrete for a dosage of 600 g/m ³ Slump Method, UNE EN 83313:1990, (cm)	5-5-6-5
Consistency of concrete for a dosage of 600 g/m ³ Vebe Test, EN ISO 12350-3:2006, (s)	9,7-11,6-13,6-16,1
Number of fibers approximately per bag of 600 g	73 x 10 ⁶

GARANTIEE

The information contained in this leaflet is based on our experience and technical knowledge, obtained through laboratory testing and from bibliographic material. **DRIZORO®, S.A.U.** reserves the right to introduce changes without prior notice. Any use of this data beyond the purposes expressly specified in the leaflet will not be the Company's responsibility unless authorised by us. We shall not accept responsibility exceeding the value of the purchased product. The data shown on consumptions, measurement and yields are for guidance only and based on our experience. These data are subject to variation due to the specific atmospheric and jobsite conditions so reasonable variations from the data may be experienced. In order to know the real data, a test on the jobsite must be done, and it will be carried out under the client responsibility. We shall not accept responsibility exceeding the value of the purchased product. For any other doubt, consult our Technical Department. This version of bulletin replaces the previous one.