



MAXFLOOR®

COMFORT SUPER

RUBBER BINDER RESIN FOR SOFT PAVEMENTS AND PLAYGROUND AREAS IN OUTDOOR USE

DESCRIPTION

MAXFLOOR® COMFORT SUPER is a transparent, one-component, solvent-free, aliphatic polyurethane resin, specifically designed to be mixed with rubber granules (SBR, EPDM, etc), cork or wood in order to provide flexible membranes and soft pavements suitable for outdoor areas where UV-resistance is required.

APPLICATIONS

- Playground areas, kinder garden, children’s games rooms, etc.
- Squares, walkways, footpaths, etc.
- Flexible and lightweight toppings on terraces, roofs, etc.
- Sport floors and soft pavements on asphalt or concrete substrates.
- Slopes on river side and artificial lakes.
- Tree pits.
- Production of preformed rubber tiles in manufacturing plants.

ADVANTAGES

- Colour stability and UV-resistance for outdoor use.
- Flexible membrane with toughness and durability.
- Continuous and seamless floors.
- It provides an open porous substrate with permeability and reduces the risk of water ponds.
- Does not change the aesthetic finish of the original rubber.
- Provides floors with impact absorption and good acoustic isolation.

- Easy mix and application, with conventional concrete mixers.
- No shrinking after cure.
- Solvent-free, non-toxic and non-flammable. Phthalate-free. Environment friendly.

APPLICATION INSTRUCTIONS

Surface preparation

Substrate must be levelled, sound, compacted, clean and with the enough mechanical strength for the expected traffic to load. Surface must be dry. It should not be exposed to raising damp. On old concrete, remove all damaged parts and loose particles to expose a structurally resistant substrate. Clean all traces of paint, dust, grease, efflorescence, gypsum, plaster, and mould release compounds.

Apply one coat by brush or roller of epoxy primer **MAXEPOX® PRIMER-W** with consumption 0,3 kg/m².

Mixing

Rubber granules must be completely dry, clean, and free of fillers, dust, salts, or any other contaminants. Mix mechanically **MAXFLOOR® COMFORT SUPER** with the granules for 3-4 minutes in a concrete mixer until achieves a homogeneous mixture free of lumps. General guideline for mixing ratio of binder:granule is as follows:

	MIXING RATIO BY WEIGHT	
	MAXFLOOR® COMFORT SUPER	GRANULES
Granule size from 1-4 mm	1	5
Granule size from 1-10 mm	1	7-9

Other mixes with different ratio binder:granule can be tested depending on size and shape of the granules used and the final properties required.

Apply immediately the mix by trowel without pressing too hard or by a straight edge, to the required layer thickness and depending on the size granule used.

Final compaction also can be done mechanically by trowelling machine. Avoid overworking the surface. Placing and finishing surface must be done within 30 minutes after mixing.

In case that a surface with less porosity finish is desired, optionally it can be applied a sealing topcoat of pure **MAXFLOOR® COMFORT SUPER** by brush or roller with consumption 0,3 kg/m² approximately.

Application conditions

Do not apply if rainfall, dew, condensation, or water contact is expected the first 24 hours. Do not apply below 10°C or if it is expected the first 24 hours. Do not apply on frozen surfaces.

Curing

Allow to dry 24-48 hours for opening to light pedestrian traffic, at 20 °C and 50% R.H. Full curing time will depend on temperature, humidity conditions and thickness layer, which can take from 3 to 4 days. In case a shorter curing time is desired, it can be added the catalyst **MAXEPOX® CAT** for very fast putting-into service.

Cleaning

Tools and equipment should be cleaned immediately with **MAXSOLVENT®** after use. Once material hardens, it can be removed only by mechanical methods.

CONSUMPTION

For a 10 mm thickness layer, it is required from 8-10 kg of the mix **MAXFLOOR® COMFORT SUPER** with granules and

depending on the size and shape granule used.

IMPORTANT INDICATIONS

- Do not add solvents or any other non-specified compound in the mix.
- Floor substrates should not be exposed to raising damp.
- For other uses not specified on this Technical Bulletin or further information, consult our Technical Department.

PACKAGING

MAXFLOOR® COMFORT SUPER is supplied in 25 kg drum and 200 kg drum, respectively.

STORAGE

Twelve months in its original unopened drum, in a dry and covered place protected from direct sunlight, humidity and frost, with temperatures between 10°C and 35°C. Storage above 35°C may result in an increase of viscosity of the resin.

SAFETY AND HEALTH

MAXFLOOR® COMFORT SUPER is a non-corrosive, non-flammable, and non-toxic product but eye and skin contact must be avoided. Use gloves and safety goggles. In case of eye contact thoroughly clean with clean water, but do not rub. In case of skin contact, wash affected areas with water and soap. If irritation persists, seek medical attention.

It is available Safety Data Sheet of **MAXFLOOR® COMFORT SUPER**.

Disposal of the product and its empty packaging must be made by the final user and according to local official regulations.

TECHNICAL DATA

Characteristics of the product	
Colour and appearance	One-component, transparent, aliphatic polyurethane resin
Solids content, (% by weight)	100
Flash point	Non-flammable
Density, (g/cm ³)	1,05 ± 0,1
Application and curing conditions	
Minimum temperature for application and curing, (°C)	>10
Pot-life at 20°C and 50% R.H., (h)	1
Curing time for light pedestrian traffic at 20°C and 10 mm thickness, (h)	24-48
Full curing time, at 20°C and 10 mm thickness, (d)	3-4
Service temperature, (°C)	From -40 to +80
Thickness/Mixing ratio/Consumption*	
Average thickness per layer, (mm)	10-20
Resin:granule mixing ratio, (by weight)	1:5
- Granule size 1-5 mm	From 1:7 to 1:9
- Granule size 1-10 mm	
Consumption of binder:granule mix per 10 mm thickness layer	8-10 kg

*This recommended ratio is for guideline only, and it can varies depending on size and shape of the granules.

GUARANTEE

The information contained in this leaflet is based on our experience and technical knowledge, obtained through laboratory testing and from bibliographic material. **DRIZORO[®], S.A.U.** reserves the right to introduce changes without prior notice. Any use of this data beyond the purposes expressly specified in the leaflet will not be the Company's responsibility unless authorised by us. We shall not accept responsibility exceeding the value of the purchased product. The data shown on consumptions, measurement and yields are for guidance only and based on our experience. These data are subject to variation due to the specific atmospheric and jobsite conditions so reasonable variations from the data may be experienced. In order to know the real data, a test on the jobsite must be done, and it will be carried out under the client responsibility. We shall not accept responsibility exceeding the value of the purchased product. For any other doubt, consult our Technical Department. This version of bulletin replaces the previous one.



DRIZORO, S.A.U.

C/ Primavera 50-52 Parque Industrial Las Monjas
28850 TORREJÓN DE ARDOZ – MADRID (SPAIN)
Tel. +34 91 676 66 76 - +34 91 677 61 75 Fax. +34 91 675 78 13
e-mail: info@drizoro.com Web site: drizoro.com